



4225 W. Ogden Ave. • Chicago, IL 60623 • Phone: (773) 522-1900

## REZI-WELD EPOXIES & POLY-GRIP ADHESIVE SYSTEM

### REZI-WELD L.V.

A two component, low viscosity, high modulus injection epoxy designed for gravity feed of pressure injection applications.

#### Specifications

ASTM C 881 TYPE I, II, IV, GRADE 1, CLASS B & C  
AASHTO M 235 TYPE I, II, IV & V, GRADE 1, CLASS B & C

#### PACKAGING & COVERAGE

10 oz. SEM Kit (Self contained, for hand or gun application)

1 gal. unit

**Coverage:** Neat 85-110 sq. ft./gal. mixed 1-1 with aggregate will yield 350 cu. Inches of grout

### REZI-WELD 1000

A two component, medium viscosity, high modulus epoxy adhesive used primarily as a bonding agent for concrete. Rezi-Weld 1000 can be extended with aggregate (One part epoxy to 1-4 parts aggregate) for patching (Not to exceed 2").

#### Specifications

ASTM C 881 TYPE I, II, GRADE 2, CLASS B & C  
AASHTO M 235 TYPE I, II, IV & V GRADE 2, CLASS B & C

#### PACKAGING & COVERAGE

One gal. units

**Coverage** (As a bonding agent):  
85-110 sq. ft/gal.

### REZI-WELD GEL

A two component, high viscosity, high modulus epoxy gel paste developed for vertical & overhead concrete surfaces (Patches, repairs, anchoring).

#### Specifications

ASTM C 881 TYPE I, II, GRADE 3, CLASS B & C  
AASHTO M 235 TYPE I, II, GRADE 3, CLASS B & C

#### PACKAGING & COVERAGE

20 oz. dual cartridge with mix nozzle

1 gal. unit

**Coverage:** One gallon provides approximately 231 cu. Inches of adhesive

### SEALTIGHT POLY-GRIP

A two component, non sag, rapid hardening polyester anchoring adhesive for structural anchoring & doweling in a wide temperature range (20°F-120°F).

#### Specifications

Consistency ASTM C 881 Non-Sag

#### PACKAGING & COVERAGE

28 oz. dual cartridge with mix nozzle  
(For 10-1 ratio gun)

**Coverage:** One cartridge yields 50 cu. inches