

# MOVEMENT JOINT PRODUCTS

## Rapid® Control Joint Rubber Compound

### Shear Strength

Control Joint Type	Average Load per 8" of Joint (lbs)	Shear Strength (psi)
Wide Flange	2350	470
Regular	2706	541

## Rapid® Poly-Joint P.V.C. Compound

### Shear Strength

Control Joint Type	Average Load per 8" of Joint (lbs)	Shear Strength (psi)
Wide Flange	2283	490
Regular	2831	566

**MASONRY**

