



4225 W. Ogden Ave. • Chicago, IL 60623 • Phone: (773) 522-1900

## CT-40 Dry Latex Mortar

### Do All Polymer Modified Repair Mortar

**CT-40 Dry Latex Mortar** is a 1 component, polymer modified, high performance concrete repair and resurfacing mortar. **CT-40 Dry Latex Mortar** is simply mixed with water and applied from featheredge to over 2" thick in one application. Apply horizontal, vertical, or overhead. Product sets in 20 to 45 minutes and ready for light traffic in 3 to 4 hours at 70°F.

#### Product Description

**CT-40 Dry Latex Mortar** is a special blend of cement, aggregate, and exclusive modifiers. Designed for general purpose and high performance concrete repair or resurfacing applications.

#### Recommended Placement Guidelines

Approximately 3-4 quarts of water is required to mix 50 lb. of product. Always add and mix product into water. For applications 2" or more, product may be extended up to 40% with clean and dry 3/8" pea gravel. Rub or scratch mixed material onto surface just prior to application.

#### Technical Data

Compressive strength	28 day Exceeds 4500 psi	ASTM C 39
Compressive strength	7 day Exceeds 3000 psi	ASTM C 39
Compressive strength	1 day Exceeds 2500 psi	ASTM C 39
Flexural Strength	28 day Over 800 psi	ASTM C 78
Freeze / Thaw Durability	Excellent	ASTM C 666
Bond Strength	Exceeds 150 psi	ACI 503 R
Color	Concrete Gray	
Working Time	15-30 minutes	

#### PACKAGING AND YIELD

**CT-40 Dry Latex Mortar** is packaged in 20 lb. pail or 50 lb. Heavy-duty polyethylene-line bags producing approximately .42 cubic feet. A 50 lb. unit of product will yield 50 square feet at 1/8".

## FormFlo P-38

### Polymer Modified Pourable Concrete

**FormFlo P-38** is a 1 component, polymer modified, high performance concrete mix. **FormFlo P-38** is simply mixed with water and applied from 3/4" thick to full depth. Product includes 3/8" aggregate, corrosion inhibitor and flow agents. Simply mix with water and pour.

#### Product Description

**FormFlo P-38** is a special blend of cement, aggregate, and exclusive modifiers. Designed for general purpose and high performance concrete repair or resurfacing applications.

#### Recommended Placement Guidelines

Approximately 3 quarts of water is required to mix 65 lb. of product. Always add and mix product into water. Hold back 1 part water and adjust at final mixing stage to desired consistency and flowability. Apply to clean and sound only. Cure per ACI guidelines or call for recommendations.

#### Technical Data

Compressive strength	28 day Exceeds 5000 psi	ASTM C39
Compressive strength	7 day Exceeds 3000 psi	ASTM C39
Air Content	6%	
Freeze / Thaw Durability	Excellent ASTM C 666	
Bond Strength	Exceeds 150 psi	ACI 503 R
Color	Concrete Gray	

#### PACKAGING AND YIELD

**FormFlo P-38** is packaged in 65 lb. Heavy-duty polyethylene-line bags producing approximately .50 cubic feet.

70-101017