

VANA TROL®

Sensitive Brick & Stone Cleaner

DESCRIPTION AND USE

Sure Klean® Vana Trol® is a concentrated acidic cleaner for new masonry surfaces that are subject to vanadium, manganese and other metallic stains. Vana Trol® is designed to simplify rinsing and reduces potential for efflorescence.

ADVANTAGES

- Clings to masonry surface, and softens excess mortar and job dirt.
- Slow-drying so it rinses clean without streaking.
- Controls green vanadium and brown manganese staining on color-sensitive brick and tile
- Safe for use on most unpolished natural stone or cast stone.
- Designed for use with colored mortar

PREPARATION

Protect people, vehicles, property, metal, painted surfaces, plants and other nonmasonry materials from product, splash, residue, wind drift and fumes. Clean masonry before installing windows, doors, finished flooring, metal fixtures, hardware, light fixtures, roofing materials and other nonmasonry items that the cleaner could harm. If already installed, protect with polyethylene before application. All caulking and sealant materials should be in place and thoroughly cured before cleaning. On new construction, masonry cleaning should be done before installation of finished flooring, metal fixtures and all other non-masonry materials. If such materials are already in place, protect with polyethylene and maintain sufficient ventilation to avoid buildup of potentially damaging fumes. New brick and tile surfaces clean most effectively 14-28 days after masonry installation. Mortar and grout smears left on the surface longer result in a more difficult cleandown and may cause undesirable results.

Surface & Air Temperature

For best results, clean when air and masonry surface temperatures are 40°F or above.

Equipment

Use low-pressure spray (50 psi max) or densely packed, soft-fibered masonry-washing brush. Rinse with high-pressure spray (400-800 psi).

APPLICATION

Before use, read "Preparation" and "Safety Information" ALWAYS TEST (minimum 4 ft. by 4 ft. area) for suitability and results before overall application. Test each type of masonry and each type of stain.

Dilutions

Dilute Vana Trol 4-10 parts water to 1 part concentrate depending on application. Adjust dilution rate based on test results. Always pour COLD water into empty polyethylene or polypropylene bucket first, then carefully add Vana Trol.

Application Instructions — Exterior

1. Thoroughly saturate the surface with fresh water.
2. Apply diluted solution freely. Do not apply Vana Trol with pressure spray above 50 psi.
3. Leave cleaning solution on the wall for about 5 minutes. Do not let cleaner dry into the masonry.
4. Reapply cleaning solution and scrape off heavy buildup of excess mortar.
5. Rinse thoroughly with fresh water, removing all cleaning compound.

SAFETY INFORMATION

Product contains hydrochloric & glycolic acids. MSDS and Spec Data sheets should be referred to prior to use.

COVERAGE & PACKAGING Available in 1 & 5 gallon containers

Substrate	Type	Use?	Coverage
Fired Clay	Brick	yes	600-900 sq. ft.
	Tile	yes	
	Terra Cotta	yes	
	Pavers	yes	
Marble, Travertine, Limestone	Polished	no	N/A
	Unpolished	yes	600-900 sq. ft.
Granite	Polished	yes	800-1000 sq. ft.
	Unpolished	yes	700-1000 sq. ft.
Sandstone	Unpolished	yes	600-900 sq. ft.
Slate	Unpolished	yes	700-1000 sq. ft.

Porous Surface Coverage: 50 sq. ft./gal. prepared
Dense/Smooth Surface Coverage: 150 sq. ft./gal prepared

Z0-1A70-10M7A